

## Development of alginate hydrogels active against adhesion of microalgae

Nassif L. Abi <sup>1,2</sup>, Rioual S. <sup>1</sup>, Trepos Rozenn <sup>3</sup>, Fauchon M. <sup>3</sup>, Farah W. <sup>2</sup>, Hellio C. <sup>3</sup>, Abboud M. <sup>2</sup>, Lescop B. <sup>1,\*</sup>

<sup>1</sup> Univ Bretagne Occidentale, Lab STICC, CNRS, UMR 6285, 6 Av Le Gorgeu, F-29285 Brest, France.

<sup>2</sup> Univ St Joseph, Fac Sci, UEGP, Beirut, Lebanon.


<sup>3</sup> Univ Bretagne Occidentale, LEMAR, BIODIMAR, UMR 6539, 6 Av Le Gorgeu, F-29285 Brest, France.

\* Corresponding author : B. Lescop, email address : [benoit.lescop@univ-brest.fr](mailto:benoit.lescop@univ-brest.fr)

### Abstract :

Microorganisms have the ability to settle on nearly all man-made surfaces in contact with seawater and subsequently to form biofilm. Biofilms control and removal is necessary in the sectors of maritime transport, energy... In this work, we present the development of new pure calcium, zinc or copper alginate, but also mixed Ca/Cu and Ca/Zn alginate hydrogels. These materials have been evaluated for their potential inhibition of adhesion of two key biofilm-forming microalgae (*Halamphora coffeaeformis* and *Cylindrotheca closterium*). All the tested materials have presented high adhesion inhibition about 80%). Copper-base materials present a high toxicity against *H. coffeaeformis*. Pure zinc alginate is also toxic for this strain. However, the addition of calcium in zinc alginate leads to the toxicity reduction. The toxicity of these materials differs according to the strains. Consequently, mixed zinc/calcium alginate are efficient at inhibiting microalgal adhesion with a low level of cells toxicity. These alginate hydrogels are promising materials because they are efficient, cheap, easy to develop and eco-friendly.

### Graphical abstract



---

## Highlights

► Elaboration of alginate hydrogels with different copper/zinc and calcium concentrations. ► High inhibition of marine microalgae adhesion by calcium, copper or zinc alginates. ► Low toxicity of mixed calcium/zinc alginate against microalgae.

**Keywords** : Biofilm, Adhesion, Alginate, Zinc, Biomaterials, Microalgae

53  
54  
55  
56  
57  
58  
59  
60  
61  
62  
63  
64  
65

## **1. Introduction**

Marine biofouling starts with the adhesion of organic molecules followed by the attachment and subsequent development of bacteria, diatoms and other microalgae,

1 which form a biofilm [1]. Adhesion and growth of macro-organisms such as macro-  
2 algae and invertebrates is then observed. This biofouling community when settled on  
3 non-treated surfaces induces a degradation process, which impacts numerous marine  
4 and industrial applications. To prevent biofouling formation, the tributyltin (TBT)  
5 biocide was extensively used in the past but is now prohibited due to its high toxicity to  
6 non-targeted marine organisms [2]. TBT has been replaced gradually by copper, mainly  
7 in its oxide or metallic form leading to pollution of seawater, mainly in marinas. Laws  
8 reducing the amount of copper in antifouling products are therefore scheduled in many  
9 countries. Thus in the United States, Washington became the first state to ban copper-  
10 based paints in the beginning of 2020 when owners of recreational boats will be  
11 prohibited to buy and apply bottom paints that contain more than 0.5% copper [3].

12 Within this context, there is an urgent need to develop new eco-friendly materials with  
13 antifouling properties.

14 Materials containing inorganic nanoparticles (NPs) have attracted research interest in  
15 recent years. In particular, numerous works focus on ZnO NPs [4-6] due to their low  
16 toxicity with respect to other biocide agents such as silver [7]. The release of both ZnO  
17 NPs from the matrix and Zn<sup>2+</sup> ions due to NPs dissolution is the key point for the  
18 optimization of antimicrobial properties. However, due to the different nature of these  
19 two processes, monitoring this release is highly difficult to realize. Producing material  
20 containing only Zn<sup>2+</sup> ions without any NPs is therefore a promising and environmental  
21 friendly solution since it allows a better optimization of the active species release.

22 Elaboration of such material is feasible by inserting Zn<sup>2+</sup> ions in anionic type materials  
23 by sorption. The antibacterial activity of Zn<sup>2+</sup> liberated from clays and alginates was  
24 recently demonstrated in the biomedical domain against bacteria and fungi [8,9]. The  
25 aim of the present study concerns the investigation of the antimicrobial property of

1 calcium, zinc and copper alginates on the growth of *Halimnobia coffeaeformis* and  
2 *Cylindrotheca closterium*, which are pioneer microalga strains involved in surface  
3  
4  
5  
6  
7  
8  
9  
10  
11  
12  
13  
14  
15  
16  
17  
18  
19  
20  
21  
22  
23  
24  
25  
26  
27  
28  
29  
30  
31  
32  
33  
34  
35  
36  
37  
38  
39  
40  
41  
42  
43  
44  
45  
46  
47  
48  
49  
50  
51  
52  
53  
54  
55  
56  
57  
58  
59  
60  
61  
62  
63  
64  
65

calcium, zinc and copper alginates on the growth of *Halimnobia coffeaeformis* and *Cylindrotheca closterium*, which are pioneer microalga strains involved in surface colonization, biofilm formation and biocorrosion [10]. Limiting the adhesion of microalgae on surfaces consists of a promising alternative approach to achieve reduction of biofilm formation. Moreover, searching for adhesion represents a more environmentally friendly approach because such products have a mode of action different from conventional biocides and present low level of cells toxicity. Thus, the present study reports the anti-adhesive property of the alginates and demonstrates the dual mode of action of the material: inhibition of growth and adhesion of microalgae.

## 2. Materials and methods

A solution of sodium alginate (Sigma Aldrich 71238) was prepared with a concentration of 50 g/L by magnetic stirring during 5 hours. Solutions of  $\text{CaCl}_2$ ,  $\text{CuSO}_4$  and  $\text{Zn}(\text{C}_4\text{H}_6\text{O}_4)$  with concentrations from  $5 \cdot 10^{-4}$  to  $0.36 \text{ mol.L}^{-1}$  were added to the sodium alginate solution in order to jellify the alginate. The solution was left for 24 hours in order to saturate the alginate with the different ions. The elaborated hydrogels were rinsed with deionized water to remove the excess of ions on the surface. Mixed alginate hydrogels have been elaborated with mixed ion concentrations. The nomenclature for these alginates is  $\text{Ca}_x\text{Zn}_y / \text{Ca}_x\text{Cu}_y$ , x and y being the concentrations of the  $\text{CaCl}_2$  and  $\text{Zn}(\text{C}_4\text{H}_6\text{O}_4) / \text{CuSO}_4$  solutions in  $\text{mol.L}^{-1}$ . The analysis of the morphology of the hydrogels and their chemical composition were performed using field emission SEM (Scanning Electron Microscopy) coupled with EDX (Energy Dispersive X-ray analysis).

For the assessment of bioactivity against microfouling organisms, both the inhibition of cell adhesion and growth were evaluated [11]. The strains used for the experimental

work are two model species commonly used in biofouling studies: *Halamphora coffeaeformis* (AC713) and *Cylindrotheca closterium* (AC170) [12]. The procedure is detailed in the electronic supplementary material.

### 3. Results and discussion

Zinc, copper and calcium alginate hydrogels were produced by immersing sodium alginate in solutions containing  $Zn^{2+}$ ,  $Cu^{2+}$  and  $Ca^{2+}$  ions. The composition of these materials was studied by EDX measurements and presented in Table 1. The materials are mainly composed of carbon and oxygen atoms due to the hydroxyl and carboxyl groups of the alginate matrix. The presence of cations in the materials is clearly noted, it can be explained by the ion exchange process between  $Na^+$  present in alginate and the cations in the solution [13]. Moreover, XPS measurements have proved the presence of  $Cu^{2+}$ ,  $Ca^{2+}$  and  $Zn^{2+}$  species. Note that 5 zones in the different parts of the gels were analyzed by EDX and the achieved results display the material composition homogeneity.

	C	O	Cu	Zn	Ca	Na
$Zn_{0.05}$	64.0	28.6		2.5		4.9
$Cu_{0.05}$	58.2	37.4	1.4			3.0
$Ca_{0.36}$	54.5	40.5			4.7	0.3

Table 1. EDX data showing the atomic percentage of each element for the different hydrogels

The influence of alginates on the adhesion and growth of microalgae was evaluated firstly towards *Halamphora coffeaeformis* (see Fig. 1 for results). Zinc alginate leads to a significant reduction of both adhesion (84%) and growth (55%). Similarly, copper alginate induces a similar level adhesion inhibition (84%) but with a significant stronger growth reduction (85%). At the concentration assessed here, both zinc and copper-alginate exhibit a dual mode of action with cells adhesion and growth inhibition. These

1 types of activities lead to efficient antifouling solutions, and undoubtedly increase the  
2 length of duration of the surface protection, as the few cells on the surface will then face  
3 a very slow growth rate from the biocidal action. However the market requirement  
4 nowadays tend to minimize as much as possible the use of biocides in the environment,  
5 thus an idea compound will have high activity on inhibition of cells adhesion but  
6 without too high biocidal action. In that view, the results obtained for calcium alginate  
7 ( $\text{Ca}_{0.36}$ ) are of high interest because we recorded significant anti-adhesive property  
8 (>85%) with lower effect on growth inhibition (25%).




Fig. 1. Growth and adhesion inhibition to *H. coffeaeformis* by zinc, copper and calcium alginate gels.

37 Following the Biocidal Products Regulation (Regulation (EU) 528/2012), antifouling  
38 candidate should work within the called “therapeutic window” with  $\text{EC}_{50}$  values  
39 (efficient concentration leading to 50% inhibition) being inferior to  $\text{LC}_{50}$  values  
40 (concentration leading to 50% mortality). From our results, it appears that the  
41 antimicrobial property of alginates can then be adjusted to reach this limit by  
42 considering alginates containing different amounts of the three considered ions. Thus,  
43 Fig. 2 presents the growth inhibition and anti-adhesive property of various mixed CaZn  
44 (or CaCu) alginate hydrogels assayed towards *Halamphora coffeaeformis* and  
45 *Cylindrotheca closterium*. The Zn (or Cu) concentration was between  $5.10^{-2}$  to  $5.10^{-4}$   
46 mol/L. For *H.coffeaeformis* (Fig. 2a,b), the influence of the alginates on the cells

adhesion is very similar to that previously found with  $Zn_{0.05}$ ,  $Cu_{0.05}$  and  $Ca_{0.36}$ . A reduction of the growth inhibition is observed for  $Zn_{0.05}Ca_{0.27}$  and  $Cu_{0.05}Ca_{0.27}$ , with respect to  $Zn_{0.05}$  and  $Cu_{0.05}$ . The inhibition growth for the  $Zn_{0.05}Ca_{0.27}$  alginate becomes lower than the 50% limit. EDX measurements have shown that the main difference between pure and mixed alginates concerns the presence of calcium ions which replace sodium ones. The reduction of the cells mortality (related to inhibition of growth) is therefore not associated with a variation of the number of  $Zn^{2+}/Cu^{2+}$  ions in the matrix. This reduction should therefore be ascribed to a different release of Zn/Cu ions between sodium and calcium alginates. This can be attributed to the solubility of the two matrices. As shown in Fig. 2(a,b), the subsequent decrease of Cu/Zn concentration does not change drastically the results.




Fig. 2. Growth and adhesion inhibition of *H.coffeaeformis* (a,b) and *Cylindrotheca* (c,d) by zinc (a,c) and copper (b,d) alginate hydrogels with different concentrations.

Fig. 2(c,d) presents the assays performed on *C. closterium*. The anti-adhesive property is similar to that already observed earlier. However, in contrast to the previous strain, a



1 clear relationship is observed between the concentration of Zn<sup>2+</sup> (Cu<sup>2+</sup>) ion in mixed  
2 alginates and the inhibition of growth. This behavior is explained by different  
3 sensitivities of microalgae to the cations and enables the development of antimicrobial  
4 materials specific to some strains.  
5  
6  
7  
8  
9

#### 10 11 **4. Conclusion**

12 Calcium, zinc and copper alginate hydrogels have been elaborated with different ion  
13 concentrations. The obtained materials have been tested on two microalgae strains:  
14 *H.coffeaformis* and *C.closterium*. All the tested materials have presented high adhesion  
15 inhibition. Mixed zinc/calcium alginate protects the surfaces by blocking the microalgae  
16 adhesion together with a low toxicity: this property is essential for an antifouling  
17 material. Consequently, these alginate hydrogels are promising materials because they  
18 are cheap, easy to develop, eco-friendly and in the therapeutic window.  
19  
20  
21  
22  
23  
24  
25  
26  
27  
28  
29  
30  
31

#### 32 33 **5. References**

- 34  
35  
36 [1] D.M. Yebra, S. Kiil, K. Dam-Johansen, Antifouling technology-past, present and future steps  
37 towards efficient and environmentally friendly antifouling coatings, Prog. Org. Coat. 50 (2004) 75-  
38 104: doi/10.1016/j.porgcoat.2003.06.001.  
39  
40  
41 [2] B. Antizar-Ladislao, Environmental levels, toxicity and human exposure to tributyltin (TBT)-  
42 contaminated marine environment. A review, Environ. Inter. 34 (2008) 292-308:  
43 doi/10.1016/j.envint.2007.09.005.  
44  
45  
46 [3] R. Trepos, E. Pinori *et al*, Innovative approaches for the development of new copper-free marine  
47 antifouling paints, J. Ship Ocean Techn. 9 (2014) 7-18.  
48  
49  
50 [4] A Sirelkhatim, S. Mahmud *et al*, Review on Zinc Oxide Nanoparticles: Antibacterial Activity and  
51 Toxicity Mechanism, Nano-micro Lett. 7 (2015) 219-242: doi/10.1007/s40820-015-0040-x  
52  
53  
54 [5] E.A.S. Dimapilis, C.S. Hsu *et al*, ZnO nanoparticles for water disinfection, Sustainable Environment  
55 Research 28 (2018) 47-56: doi/10.1016/j.serj.2017.10.001.  
56  
57  
58  
59  
60  
61  
62  
63  
64  
65

- 1  
2  
3  
4  
5  
6  
7  
8  
9  
10  
11  
12  
13  
14  
15  
16  
17  
18  
19  
20  
21  
22  
23  
24  
25  
26  
27  
28  
29  
30  
31  
32  
33  
34  
35  
36  
37  
38  
39  
40  
41  
42  
43  
44  
45  
46  
47  
48  
49  
50  
51  
52  
53  
54  
55  
56  
57  
58  
59  
60  
61  
62  
63  
64  
65
- [6] L. Cordero-Arias, S. Cabanas-Polo *et al*, Electrophoretic deposition of ZnO/alginate and ZnO-bioactive glass/alginate composite coatings for antimicrobial applications, *Mater. Sci. Eng. C*, 55 (2015) 137-144: doi.org/10.1016/j.msec.2015.05.034
- [7] J. Pandiarajan, M. Krishnan, Properties, synthesis and toxicity of silver nanoparticles, *Environ. Chem. Lett.*, 15 (2017) 387-397: doi/10.1007/s10311-017-0624-4
- [8] M.C. Straccia, G.G. d'Ayala *et al*, Novel zinc alginate hydrogels prepared by internal setting method with intrinsic antibacterial activity, *Carbohydrate Polymers*, 125 (2015) 103-112: doi/10.1016/j.carbpol.2015.03.010.
- [9] F.D. Velázquez-Herrera, G. Fetter *et al*, Effect of structure, morphology and chemical composition of Zn-Al, Mg/Zn-Al and Cu/Zn-Al hydrotalcites on their antifungal activity against *A. niger*, *J. Environ. Chem. Eng.* 6 (2018) 3376-3383: doi.org/10.1016/j.jece.2018.04.069
- [10] J.F. Briand, I. Djeridi *et al*, Pioneer marine biofilms on artificial surfaces including antifouling coatings immersed in two contrasting French Mediterranean coast sites, *Biofouling* 28 (2012) 453-463: doi/10.1080/08927014.2012.688957
- [11] R. Trepos, G. Cervin *et al*, Antifouling Compounds from the Sub-Arctic Ascidian *Synoicum pulmonaria*: Synoxazolidinones A and C, Pulmonarins A and B, and Synthetic Analogues, *J. Nat. Prod.* 77 (2014) 2105-2113: doi/10.1021/np5005032
- [12] L. Moodie, G. Cervin *et al*, Design and Biological Evaluation of Antifouling Dihydrostilbene Oxime Hybrids, *Marine Biotech.* 20 (2018) 257-267: doi/10.1007/s10126-018-9802-z
- [13] G. Germanos, S. Youssef *et al*, Diffusion and agglomeration of Fe oxide NP in magnetic calcium alginate beads initiated by Cu sorption, *J. Environ. Chem. Eng.* 5 (2017) 3727-3733: doi/10.1016/j.jece.2017.07.033

## Figures and captions




Fig. 1. Growth and adhesion inhibition to *H. coffeaeformis* by zinc, copper and calcium alginate gels.




Fig. 2. Growth and adhesion inhibition of *H.coffeaeformis* (a,b) and *Cylindrotheca* (c,d) by zinc (a,c) and copper (b,d) alginate hydrogels with different concentrations.

**Table**

	C	O	Cu	Zn	Ca	Na
Zn <sub>0.05</sub>	64.0	28.6		2.5		4.9
Cu <sub>0.05</sub>	58.2	37.4	1.4			3.0
Ca <sub>0.36</sub>	54.5	40.5			4.7	0.3

Table 1. EDX data showing the atomic percentage of each element for the different hydrogels